Amendments to the Claims

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims

Claims 1-20 (Previously cancelled)

- 21. (Currently amended) A method of melt processing a polypropylene blend, the method comprising providing a multimodal bimodal polypropylene blend in a molten state, said blend comprising from 50 to 70 wt.% of a first high molecular weight fraction and from 50 to 30 wt.% of a second low molecular weight fraction and having a melt dispersion index of from 8 to 70 and a ratio Mz/Mn of at least 10 thereby enhancing a compromise between melt strength and drawability, and processing the blend in the melt by drawing and cooling the blend to form a solid product.
- 22. (Previously presented) A method according to claim 21 wherein the dispersion index is greater than 15.
- 23. (Previously presented) A method according to claim 21 wherein the ratio of Mz/Mn is from 50-150.
- 24. (Previously presented) A method according to claim 23 wherein the dispersion index is greater than 15.
 - 25. (Cancelled)
 - 26. (Cancelled)

- 27. (Previously presented) A method according to claim 21 wherein the blend comprises from 55 to 60 wt.% of the first fraction and from 45 to 35 wt.% of the second fraction.
- 28. (Currently amended) A-method according to claim 21 A method of melt processing a polypropylene blend, the method comprising providing a multimodal polypropylene blend in a molten state, said blend having a melt dispersion index of from 8 to 70 and a ratio Mz/Mn of at least 10 thereby enhancing a compromise between melt strength and drawability, and processing the blend in the melt by drawing and cooling the blend to form a solid product wherein the blend has been formed by reactive extrusion of a mixture of at least two fractions together with a mixture of a chain scission agent and a chain grafting agent.
- 29. (Previously presented) A method according to claim 28 wherein the chain scission agent comprises 2,5-dimethyl-2,5-di(tert-butylperoxy) hexane.
- 30. (Previously presented) A method according to claim 28 wherein the chain grafting agent is selected from the group consisting of allyl methacrylate and divinyl benzene.
 - 31. (Cancelled)
 - 32. (Cancelled)
 - 33. (Cancelled)
 - 34. (Cancelled)
 - 35. (Cancelled)
- 36. (Currently amended) A multimodal polypropylene blend according to claim 35 42 wherein the dispersion index is greater than 15.

- 37. (Currently amended) A multimodal polypropylene blend according to claim 33 polypropylene blend useful in melt processing and providing for enhancing a compromise between melt strength and drawability, said blend having a dispersion index of at least 8 and a ratio Mz/Mn of at least 10, wherein the blend is bimodal and comprises from 50 to 70 wt.% of a first high molecular weight fraction and from 50 to 30 wt.% of a second low molecular weight fraction.
- 38. (Previously presented) A multimodal polypropylene blend according to claim 37 wherein the ratio of the melt flow indexes of the first and second fractions is at least 5.
- 39. (Previously presented) A multimodal polypropylene blend according to claim 37 wherein the blend comprises from 55 to 65 wt.% of the first fraction and from 45 to 35 wt.% of the second fraction.
- 40. (Previously presented) A multimodal polypropylene blend according to claim 39 wherein the ratio of the melt flow indexes of the first and second fractions is at least 5.
- 41. (New) A multimodal polypropylene blend useful in melt processing and providing for enhancing a compromise between melt strength and drawability, said blend having a dispersion index greater than 15 and a ratio Mz/Mn of at least 10.
- 42. (New) A multimodal polypropylene blend useful in melt processing and providing for enhancing a compromise between melt strength and drawability, said blend having a dispersion index of at least 8 and a ratio Mz/Mn of from 50 150.